

DATE RELEASED FROM LAB	: 2016.10.19	FABRIC TYPE - WOVEN	: 4/1 Satin
QUALITY	: CS59	COMPOSITION	: 100% Cotton
FINISH	: W12	WARP COUNT (tex)	: 42
INVOICE NUMBER	: 421589	WEFT COUNT (tex)	: 60

		ACTUAL PERFORMANCE	Da Gama Specification	SABS 1387-IV
Dispo	:	1825160400		D59
Shade / Design	:	2004		
Weave	Visual Examination	4/1 Satin	4/1 Satin	4/1 Satin
Width (cm)	:	154	151	
Composition		100 % Cotton	100 % Cotton	100 % Cotton
Ends / Picks	SANS method 7211-2 :	38/19	37/17	37/17
Mass (g/m)	SANS method 79 :	286	270	270
Dimensional Stability	SANS method 960 : Warp Washing procedure A	-1.2	2.0	2.0
	Drying Procedure E : Weft	-1.6	2.0	2.0
Breaking Strength (N)	SANS method 13934-1 : Warp	1233	940	940
	: Weft	467	510	510
Colour Fastness to Washing	SANS method 11166 Procedure C :	Colour	4/5	4
		Staining	4/5	4
Colour Fastness to Perspiration	SABS ISO 105-E04 1994 (Multi fiber Adjacent used)	Persp Acid	5	4/5
		Persp Alk	5	4/5
Light	SANS method 105 - B02 :	4	4	4
Flame Retardancy	SABS 1423-1/1987	PASSED		

RESULTS - PASSED

EDCON CORRELATED
ISO 9001: 2008
WOOLWORTHS CORRELATED

Date test report generated : 2017.01.11
Contact Person : Siphokazi Mbatani
Telephone No : 040 - 608 6356
Fax : 040 - 608 6291