

DATE RELEASED FROM LAB	:	2016.12.05	FABRIC TYPE - WOVEN	:	2/1 Twill
QUALITY	:	CJ 54	COMPOSITION	:	100% Cotton
FINISH	:	W1	WARP COUNT (tex)	:	42
INVOICE NUMBER	:	421638	WEFT COUNT (tex)	:	42

		ACTUAL PERFORMANCE	Da Gama Specification	SABS 1387-IV
Dispo	:	1824960100		J54
Shade / Design	:	2003		
Weave	Visual Examination	2/1 Twill	2/1 Twill	2/1 Twill
Width (cm)	:	149	151	
Composition		100 % Cotton	100 % Cotton	100 % Cotton
Ends / Picks	SANS method 7211-2 :	36/20	32/17	32/17
Mass (g/m)	SANS method 79 :	235	220	220
Dimensional Stability	SANS method 960 Washing procedure A Drying Procedure E	Warp	+1.6	2.0
		Weft	-0.5	2.0
Breaking Strength (N)	SANS method 13934-1	Warp	1032	770
		Weft	371	425
Colour Fastness to Washing	SANS method 11166 Procedure C	Colour	4/5	4
		Staining	4	4
Light	SANS method 105 - B02 :	4	4	4

**RESULTS - PASSED**

EDCON CORRELATED  
ISO 9001: 2008  
WOOLWORTHS CORRELATED

Date test report generated : 2017.01.11  
Contact Person : Siphokazi Mbatani  
Telephone No : 040 - 608 6356  
Fax : 040 - 608 6291